



TECHNICAL INFORMATION

<u>1. PRODUCT NAME</u>	ANOPRIME
<u>2. USES</u>	Aqueous Pigmented Stoving Anti-Corrosive Primer
<u>3. REFERENCE</u>	6WB-2-1213
<u>4. COLOUR</u>	Yellow
<u>5. COMPOSITION</u>	Crosslinking resin + anti-corrosive (chrome free) pigments.
<u>6. APPLICATION</u>	Conventional spray equipment, airless, electrostatic spray suitable for water based. Recommended dry film weight 10-12 microns.
<u>7. VISCOSITY</u>	Supply viscosity 100 +/-5 secs B4 cup @ 20°C Recommended application viscosity as supplied. 10% water may be added if required.
<u>8. SOLIDS</u>	28% +/- 2%
<u>9. DENSITY</u>	1.13 – 1.19
<u>10. VOC'S</u>	Less than 20 grms/litre
<u>11. STOVING</u>	180°C 10 – 15 mins M.T.
<u>12.STORAGE</u>	Must be kept in an area with a minimum temperature of 5°C.

Legal Note: Please note that due to factors beyond our control (including cleanliness of metal and baking cycle etc), we do not offer any warranties or guarantees regarding the overall performance of incorporating **Anoprime** into a powder coating system and it is therefore left to the individual/company to assess for themselves that the use of **Anoprime** will be beneficial.